

















FEATURE CARATTERISTICA DATEN CARACTÉRISTIQUE		TECHNICAL FEATURES CARATTERISTICHE TECNICHE TECHNISCHE DATEN CARACTÉRISTIQUES TECHNIQUES	STANDARD NORMA NORM NORME	ESTABLISHED LIMITS LIMITI PREVISTI VORGESEHENE GRENZWERTE LIMITES ÉTABLIES		OUTDOOR WOOD 2 CM
<b>REGULARITY</b> REGOLARITÀ REGELMÄßIGKEIT RÉGULARITÉ		<b>LENGHT AND WIDTH</b> LUNGHEZZA E LARGHEZZA LÄNGE UND BREITE LONGUEUR ET LARGEUR	ISO 10545-2	± 0.6 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>THICKNESS</b> SPESSORE DICKE ÉPAISSEUR	ISO 10545-2	± 5.0 %	± 0.5 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>RECTANGULARITY</b> ORTOGONALITÀ RECHTWINKLIGKEIT PERPENDICULARITÉ	ISO 10545-2	± 0.5 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>STRAIGHTNESS OF SIDES</b> RETTILINEITÀ DEGLI SPIGOLI GERADLINIGKEIT DER KANTEN RECTITUDE DES ARETES	ISO 10545-2	± 0.5 %	± 1.5 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>SURFACE FLATNESS</b> PLANARITÀ EBENFLÄCHIGKEIT PLANEITE DE SURFACE	ISO 10545-2	± 0.5 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
<b>STRUCTURAL</b> STRUTTURALE STRUKTURELL STRUCTURAL		<b>WATER ABSORPTION</b> ASSORBIMENTO D'ACQUA WASSERAUFNAHME ABSORPTION D'EAU	ISO 10545-3	≤ 0.5 %		<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>BREAKING STRENGHT</b> SFORZO DI ROTTURA BRUCHFESTIGKEIT FORCE DE RUPTURE	ISO 10545-4	≥ 1300 N		>10000 N
		<b>MODULUS OF RUPTURE</b> MODULO DI ROTTURA BRUCHMODUL MODULE DE RUPTURE	ISO 10545-4	≥ 35 N/mm <sup>2</sup>		≥ 35 N/mm <sup>2</sup>
<b>SURFACE</b> SUPERFICIE OBERFLÄCHE SURFACE		<b>ABRASION RESISTANCE</b> RESISTENZA ALL'ABRASIONE ABRIEBFESTIGKEIT RESISTANCE A L'ABRASION	ISO 10545-7	CLASS DECLARED CLASSE DICHIARATA KLASSE ERKLÄRT CLASSE DÉCLARÉ		H Grigio: 3, 1500 rp H Marrone: 3, 750 rp H Noce: 4, 2100 rp
<b>THERMAL HYGROMETRIC</b> TERMO IGROMETRICHE THERMAL HYGROMETRISCH THERMIQUE HYGROMÉTRIQUE		<b>LINEAR THERMAL-EXPANSION</b> DILATAZIONE TERMICA LINEARE LINEARER WÄRMEAUSDEHNUNG DILATATION THERMIQUE LINEAIRE	ISO 10545-8	VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE		α ≤ 9 · 10 <sup>-6</sup> °C
		<b>THERMAL SHOCK RESISTANCE</b> RESISTENZA AGLI SBALZI TERMICI WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE	ISO 10545-9	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>FROST RESISTANCE</b> RESISTENZA AL GELO FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL	ISO 10545-12	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>REACTION TO FIRE</b> REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	EN 14411	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>A1 FL / A1</b>

Product, Prodotto, Produkt, Produit: OUTDOOR WOOD 2 CM HARENA

Rev: 10/11/2021

<b>CHEMICAL</b> CHIMICA CHEMISCH CHIMIQUE		<b>RESISTANCE TO CHEMICALS (ACIDS, BASES AND SALTS)</b> RESISTENZA ALL'ATTACCO CHIMICO (ACIDI, BASI E SALI) CHEMIKALIENBESTÄNDIGKEIT (SÄUREN, BASIS UND SALZ) RESISTANCE A L'ATTAQUE CHIMIQUE (ACIDES, BASES ET SELS)	<b>ISO 10545-13</b>	<b>UB MINIMUM</b> UB MINIMO UB MINIMUM UB MINIMUM	<b>A HA LA GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>RESISTANCE TO STAINS</b> RESISTENZA ALLE MACCHIE FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES	<b>ISO 10545-14</b>	<b>≥ 3</b>	<b>5 GUARANTEED</b> 5 GARANTITO 5 GARANTIERT 5 GARANTI
<b>SAFETY</b> SICUREZZA SICHERHEIT SÉCURITÉ		<b>SKID RESISTANCE</b> RESISTENZA ALLO SCIVOLAMENTO RUTSCHHEMMUNG RÉSISTANCE AU GLISSEMENT	<b>DIN 51130</b>	<b>VALUE DECLARED</b> VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE	<b>R11</b>
			<b>DIN 51097</b>		<b>A+B</b>
		<b>REACTION TO FIRE</b> REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	<b>EN 13501-1</b>	<b>CLASS DECLARED</b> CLASSE DICHIARATA KLASSE ERKLÄRT CLASSE DÉCLARÉ	<b>A1 FL / A1</b>

**Compliant with standards EN 14411 (ISO 13006) annex G group B1a  
Conforme alla norma EN 14411 (ISO 13006) Appendice G gruppo B1a**