

SOLAR REFLECTANCE INDEX (SRI) REFLECTANCE (r_{sol})

Product: SUPER HARD KERAMIK 3 CM Listone Grigio

Rev: 01/02/2023

Test specimen

Campione

SUPER HARD KERAMIK 3 CM Listone Grigio



Test method

Metodo di test

Spectrophotometer

Spettrofotometro

Test result

Risultato del test

SRI = 31

ϵ = 0,878

r_{sol} = 0.297

Under our responsibility we declare that the declared value is reliable and measured according to the highest standards available at present with calibrated instruments suitable for the application complying the standard ASTM E 1980-01.

Sotto la nostra responsabilità dichiariamo che il valore dichiarato è attendibile e misurato secondo i più alti standard disponibili allo stato attuale con strumentazioni tarate e idonee all'applicazione secondo lo standard ASTM E 1980-01.

Ing. Alberto Sottocornola

Quality

Granulati Zandobbio S.p.A.

Via Selva, 29

24060 ZANDOBBIO (Bergamo)

Tel. +39.035.941584 – Fax. +39.035.944766

Codice Fiscale e Partita IVA 01368480164

www.granulati.it E-mail: info@granulati.it