

SOLAR REFLECTANCE INDEX (SRI) REFLECTANCE (r_{sol})


Product: L'ALTRA PIETRA[®] Castello Grey

Rev: 01/02/2023

Test specimen

Campione

L'ALTRA PIETRA Castello Grey



Test method

Metodo di test

Spectrophotometer

Spettrofotometro

Test result

Risultato del test

SRI = 38

ϵ = 0,90

r_{sol} = 0,35

Under our responsibility we declare that the declared value is reliable and measured according to the highest standards available at present with calibrated instruments suitable for the application complying the standard ASTM E 1980-01.

Sotto la nostra responsabilità dichiariamo che il valore dichiarato è attendibile e misurato secondo i più alti standard disponibili allo stato attuale con strumentazioni tarate e idonee all'applicazione secondo lo standard ASTM E 1980-01.

Ing. Alberto Sottocornola
Quality

Granulati Zandobbio S.p.A.

Via Selva, 29
24060 ZANDOBBIO (Bergamo)
Tel. +39.035.941584 – Fax. +39.035.944766
Codice Fiscale e Partita IVA 01368480164
www.granulati.it E-mail: info@granulati.it