

SOLAR REFLECTANCE INDEX (SRI) REFLECTANCE (r_{sol})


Product: L'ALTRA PIETRA® Fortezza Maggia

Rev: 01/02/2023

Test specimen

Campione

L'ALTRA PIETRA Fortezza Maggia



Test method

Metodo di test

Spectrophotometer
Spettrofotometro

Test result

Risultato del test

SRI = 27

ϵ = 0,865

r_{sol} = 0,273

Under our responsibility we declare that the declared value is reliable and measured according to the highest standards available at present with calibrated instruments suitable for the application complying the standard ASTM E 1980-01.

Sotto la nostra responsabilità dichiariamo che il valore dichiarato è attendibile e misurato secondo i più alti standard disponibili allo stato attuale con strumentazioni tarate e idonee all'applicazione secondo lo standard ASTM E 1980-01.

Ing. Alberto Sottocornola
Quality

Granulati Zandobbio S.p.A.

Via Selva, 29
24060 ZANDOBBIO (Bergamo)
Tel. +39.035.941584 – Fax. +39.035.944766
Codice Fiscale e Partita IVA 01368480164
www.granulati.it E-mail: info@granulati.it