

# SOLAR REFLECTANCE INDEX (SRI) REFLECTANCE ( $r_{sol}$ )

Product: L'ALTRA PIETRA® Colosseo Barge

Rev: 22/03/2019

## Test specimen

### Campione

L'ALTRA PIETRA Colosseo Barge



## Test method

### Metodo di test

Spectrophotometer

Spettrofotometro

## Test result

### Risultato del test

SRI = 47

$\epsilon$  = 0,90

$r_{sol}$  = 0,42

Under our responsibility we declare that the declared value is reliable and measured according to the highest standards available at present with calibrated instruments suitable for the application complying the standard ASTM E 1980-01.

Sotto la nostra responsabilità dichiariamo che il valore dichiarato è attendibile e misurato secondo i più alti standard disponibili allo stato attuale con strumentazioni tarate e idonee all'applicazione secondo lo standard ASTM E 1980-01.

Ing. Alberto Sottocornola

Quality

**Granulati Zandobbio S.p.A.**

Via Selva, 29

24060 ZANDOBBIO (Bergamo)

Tel. +39.035.941584 – Fax. +39.035.944766

Codice Fiscale e Partita IVA 01368480164

www.granulati.it E-mail: info@granulati.it