

# SOLAR REFLECTANCE INDEX (SRI) REFLECTANCE ( $r_{sol}$ )

Product: L'ALTRA PIETRA® Fortezza Biasca

Rev: 01/02/2023

## Test specimen

### Campione

L'ALTRA PIETRA Fortezza Biasca



## Test method

### Metodo di test

Spectrophotometer  
Spettrofotometro

## Test result

### Risultato del test

SRI = 45

$\epsilon$  = 0,888

$r_{sol}$  = 0,405

Under our responsibility we declare that the declared value is reliable and measured according to the highest standards available at present with calibrated instruments suitable for the application complying the standard ASTM E 1980-01.

Sotto la nostra responsabilità dichiariamo che il valore dichiarato è attendibile e misurato secondo i più alti standard disponibili allo stato attuale con strumentazioni tarate e idonee all'applicazione secondo lo standard ASTM E 1980-01.

Ing. Alberto Sottocornola  
Quality

**Granulati Zandobbio S.p.A.**

Via Selva, 29  
24060 ZANDOBBIO (Bergamo)  
Tel. +39.035.941584 – Fax. +39.035.944766  
Codice Fiscale e Partita IVA 01368480164  
www.granulati.it E-mail: info@granulati.it